

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : C08F 4/62, 4/70, 10/02, C07F 19/00, C07C 257/14, C07F 7/10	A1	(11) International Publication Number: WO 00/12568 (43) International Publication Date: 9 March 2000 (09.03.00)
(21) International Application Number: PCT/US99/19954 (22) International Filing Date: 31 August 1999 (31.08.99) (30) Priority Data: 60/098,668 1 September 1998 (01.09.98) US (71) Applicant (for all designated States except US): E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): ITTEL, Steven, Dale [US/US]; 7 Barley Mill Drive, Wilmington, DE 19807 (US). COUGHLIN, Edward, Bryan [US/US]; 30 Orchard Street, Amherst, MA 01002 (US). WANG, Ying [CN/US]; 1347 Wooded Knoll, West Chester, PA 19382 (US). (74) Agent: EVANS, Craig, H.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).		(81) Designated States: AE, AL, AU, BA, BB, BG, BR, CA, CN, CR, CU, CZ, EE, GD, GE, HR, HU, ID, IL, IN, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ, VN, YU, ZA, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: POLYMERIZATION OF OLEFINS (57) Abstract Olefins such as ethylene and propylene may be polymerized by using as catalysts novel selected transition metal complexes of bis (carboximidamidatonates) in which the carboximidamidatonate groups are connected together through covalent bonds by a bridging group. The resulting polymers are useful as molding and extrusion resins.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

TITLE

POLYMERIZATION OF OLEFINS

FIELD OF THE INVENTION

5 Olefins are polymerized by using as polymerization catalysts certain novel transition metal complexes of selected bis(carboximidamidonates).

TECHNICAL BACKGROUND

10 The polymerization of olefins such as ethylene, propylene, norbornene and cyclopentene are very important commercial processes. These are most commonly done using polymerization catalyst systems containing certain transition complexes. For instance, the Ziegler-Natta-type catalysts
15 and metallocene-type catalysts are some of the more important and well-known catalysts of this type which are used to make billions of kilograms of polyolefins annually. Due to the importance of the polymerization of olefins, new catalyst systems are constantly being sought.

20 Japanese Patent Application 10/36,424 shows a formula for a bis(carboximidamidonate), but neither describes how to make such a compound nor actually does a polymerization with such a compound.


25 A. Littke, et al., Organometallics, vol. 17, p. 446-451 (1998); V. Volkis, et al., *ibid*, p. 3155-3157; J. C. Flores, et al., Organometallics, vol. 14, p. 2106-2108 (1995); P. J. Stewart, et al., *ibid*, p. 3271-3281; H. W. Roesky, et al., Chem. Ber., vol. 121, p. 1403-1406 (1988); and D. Herskovics-Korine, et al., J. Organometal. Chem., vol. 503, p. 307-314
30 (1995); report the synthesis and/or use of transition metal complexes of two independent (mono)carboximidamidonate ligands as polymerization catalysts. However, in none of these references are the two carboximidamidonates groups joined by a common moiety such as a benzene ring.

35 A. Littke, et al., Organometallics, vol. 17, p. 446-451 (1998) and S. L. Aelits, et al., *ibid*, p. 3265-3270, describes the formation of carboximidamidonates by the reaction of an organometallic compound with a carbodiimide.

The use of a bis(alkyl metal salt) to form a bis(carboximidamidatonate) is not described.

SUMMARY OF THE INVENTION

5 This invention concerns a first process for the polymerization of olefins, comprising the step of contacting, at a temperature of about -50°C to about $+250^{\circ}\text{C}$, (a) an olefin selected from the group consisting of an α -olefin, a styrene, a cyclopentene, and a norbornene; and (b) a catalyst
10 component for the polymerization of the olefin, characterized in that the catalyst component comprises a first compound of the formula (X)



wherein:

15 R^1 , R^2 , R^3 and R^4 are each independently hydrocarbyl, substituted hydrocarbyl or silyl;

R^{15} is a divalent organic moiety;

each X is independently an anion;

n is an integer equal to the valence of M minus 2; and

20 M is Ti, Zr, Hf, V, Cr, Sc, Y or a rare earth metal.


Optionally, the catalyst component comprises a second compound W, which is a neutral Lewis acid capable of abstracting an X^- from the first compound to form WX^- , provided that the anion formed is a weakly coordinating
25 anion, or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion; and provided that when none of X is alkyl, acyl or hydride, said second compound is capable of transferring hydride or alkyl to M.

30 This invention also concerns the first compound (X) described above.

In another aspect, the present invention concerns a second process for the polymerization of olefins, comprising

the step of contacting, at a temperature of about -50°C to about $+250^{\circ}\text{C}$, (a) an olefin selected from the group consisting of an α -olefin, a styrene, a cyclopentene, and a norbornene; and (b) a catalyst component for the

polymerization of the olefin, characterized in that the catalyst component comprises a transition metal complex of a ligand of the formula (XI)



wherein:

said transition metal is Ti, Zr, Hf, V, Cr, Sc, Y or a rare earth metal;

R^1 , R^2 , R^3 and R^4 are each independently hydrocarbyl, substituted hydrocarbyl or silyl; and

R^{15} is a divalent organic moiety.

The present invention further concerns an anion which is the ligand of the formula (XI) described above.


In yet another aspect, the present invention concerns a process for preparing a transition metal complex of a bis(carboximidamidonate), such as used in the first and second processes described above, comprising the step of reacting a salt of said transition metal with a dialkali metal salt and/or alkaline earth metal salt of a bis(carboximidamidonate).

Still further, the invention concerns a process for the production of a bis(carboximidamidonate), comprising the step of reacting a bis(alkyl metal salt) with 2 moles of a carbodiimide.

DETAILS OF THE INVENTION

Herein certain terms are used to define certain chemical groups or compounds. These terms are defined below.

- By a carboximidamidonate group is meant a group of the formula (IX)



wherein each R^{13} is independently hydrocarbyl, substituted hydrocarbyl or silyl. A bis(carboximidamidatonate) has two such groups in the molecule.

5 • By a bis(alkyl metal salt) is meant a compound which has 2 alkyl carbon atoms which each have a single negative charge and are anions of or associated with one or more metal cations in such a way that the positive charge on the metal cation(s) is balanced by the 2 negative charges on the anion.

10 • A "hydrocarbyl group" is a univalent group containing only carbon and hydrogen. If not otherwise stated, it is preferred that hydrocarbyl groups herein contain 1 to about 30 carbon atoms.

15 • By "substituted hydrocarbyl" herein is meant a hydrocarbyl group which contains one or more substituent groups which are inert under the process conditions to which the compound containing these groups is subjected. The substituent groups also do not substantially interfere with the process. If not otherwise stated, it is preferred that substituted hydrocarbyl groups herein contain 1 to about 30 carbon atoms. Included in the meaning of "substituted" are heteroaromatic rings. All of the hydrogen atoms in the substituted hydrocarbyl may be substituted for, such as in trifluoromethyl.

25 • By relatively noncoordinating (or weakly coordinating) anions are meant those anions as are generally referred to in the art in this manner, and the coordinating ability of such anions is known and has been discussed in the literature, see for instance W. Beck., et al., Chem. Rev., vol. 88 p. 1405-1421 (1988), and S. H. Stares, Chem. Rev., vol. 93, p. 927-942 (1993), both of which are hereby included by reference. Among such anions are those formed from aluminum compounds such as those described in the immediately subsequent paragraph and X^- , including $\text{R}^{19}_3\text{AlX}^-$, $\text{R}^{19}_2\text{AlClX}^-$,


30

35

$R^{19}AlCl_2X^-$, and $R^{19}AlOX^-$, wherein R^{19} is alkyl. Other useful noncoordinating anions include BAF^- {BAF = tetrakis[3,5-bis(trifluoromethyl)phenyl]borate}, SbF_6^- , PF_6^- , and BF_4^- , trifluoromethanesulfonate, p-toluenesulfonate, $(R_fSO_2)_2N^-$, and $(C_6F_5)_4B^-$.

• By an alkyl aluminum compound is meant a compound in which at least one alkyl group is bound to an aluminum atom. Other groups such as alkoxide, oxygen, and halogen may also be bound to aluminum atoms in the compound.

• By "hydrocarbylene" herein is meant a divalent group containing only carbon and hydrogen. Typical hydrocarbylene groups are $-(CH_2)_4-$, $-CH_2CH(CH_2CH_3)CH_2CH_2-$ and




(IV).

If not otherwise stated, it is preferred that hydrocarbylene groups herein contain 1 to about 30 carbon atoms.

• By "substituted hydrocarbylene" herein is meant a hydrocarbylene group which contains one or more substituent groups which are inert under the process conditions to which the compound containing these groups is subjected. The substituent groups also do not substantially interfere with the process. If not otherwise stated, it is preferred that substituted hydrocarbylene groups herein contain 1 to about 30 carbon atoms. Included within the meaning of "substituted" are heteroaromatic rings.


• By a styrene herein is meant a compound of the formula



(V)


wherein R^{26} , R^{27} , R^{26} , R^{29} and R^{30} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl or a functional group, all of which are inert in the polymerization process. It is preferred that all of R^{26} , R^{27} , R^{26} , R^{29} and R^{30} are hydrogen.

- By "a norbornene" is meant that the monomer is characterized by containing at least one norbornene-functional group in its structure including norbornadiene as identified by the formulas below, which can be substituted or unsubstituted



wherein "a" represents a single or double bond.

Representative monomers are compounds (VII) and (VIII) as follows:






- wherein R^{46} , R^{47} , R^{48} , and R^{49} independently are hydrogen halogen, or hydrocarbyl, provided that, except if the hydrocarbyl group is vinyl, if any of the hydrocarbyl are alkenyl, there is no terminal double bond, i.e., the double bond is internal; or R^{46} and R^{48} taken together can be part of carbocyclic ring (saturated, unsaturated or aromatic); or R^{46} and R^{47} and/or R^{48} and R^{49} taken together are an alkylidene group. In these structures "z" is 1 to 5. Examples of such norbornenes include norbornadiene, 2-norbornene, 5-methyl-2-norbornene, 5-hexyl-2-norbornene, 5-ethylidene-2-norbornene, vinylnorbornene, dicyclopentadiene, dihydrodicyclopentadiene, tetracyclododecene, trimers of cyclopentadiene, halogenated norbornenes wherein R^{46} , R^{47} , R^{48} and R^{49} may also be halogen or fully halogenated alkyl groups such as C_wF_{2w+1} wherein w is 1 to 20, such as perfluoromethyl and perfluorodecyl. The halogenated norbornenes can be synthesized via the Diels-Alder reaction of cyclopentadiene an appropriate dieneophile, such as $F_3CC=CCF_3$ or $R^{49}_2C=CR^{49}C_wF_{2w+1}$ wherein each R^{49} is independently hydrogen or fluorine and w is 1 to 20.

- By "saturated hydrocarbyl" is meant a univalent group containing only carbon and hydrogen which contains no


• By a silyl group is meant a group of the formula $-\text{SiR}^{16}\text{R}^{17}\text{R}^{18}$, wherein R^{16} , R^{17} and R^{18} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or a functional group.


5 The bis(carboximidamidonates) can generally be made by the following method. A dialkali metal or alkaline earth metal salt is prepared, such as is shown in equation (1), from a suitable dihalogen compound or other suitable precursor. Such reactions to prepare these types of
10 organometallic compounds are known in the art to prepare, for example, dilithium or dimagnesium compounds, see for instance G. Wilkinson, et al., Ed., Comprehensive Organometallic Chemistry, Pergamon Press, Oxford, 1982; J. Klein, et al., Tetrahedron, vol. 132, p. 51 (1976); and M. F. Lappert, et
15 al., J. Chem. Soc. Chem. Commun, p. 14 (1982). The dialkali metal salt or alkaline earth metal salt is then reacted with 2 moles of a carbodiimide to form the corresponding alkali or alkaline earth metal salt of the bis(carboximidamidonate), as shown in equation (2). The product of equation (2) is
20 then reacted with a salt of an appropriate transition metal to form the transition metal complex of the bis(carboximidamidonate) which may be used in the polymerization catalyst system. The use of a
25 bis(carboximidamidonate) (particularly the compound with a nontransition metal, such as an alkali metal or magnesium) to react with the salt of a transition metal is also novel, and preferably takes place in solution at a temperature of about -50°C to about $+100^{\circ}\text{C}$. By using appropriate groups or substituents on the various reactants, substituted
30 bis(carboximidamidonates) with different groups may be formed. Equations (1), (2) and (3) just illustrate one particular method of making these compounds.






5. In (X) and (XI) useful groups for R^{15} include, for example, $-CR^{16}_2(CR^{16}_2)_qCR^{16}_2-$ (XV), wherein each R^{16} is independently hydrogen, hydrocarbyl or substituted hydrocarbyl and q is 0 or an integer from 1 to 20, especially q is 4. Other useful groups for R^{15} include, for example, o-phenylene, 1,2-naphthylene, 2,3-naphthylene, 1,8-naphthylene, 1,2-cyclohexylene,






(XXIII) and




(XXV)

wherein R^5 , R^6 , R^7 and R^8 are each independently hydrogen, hydrocarbyl or substituted hydrocarbyl, provided that either
 5 or both of the pairs R^5 and R^6 , and R^7 and R^8 taken together may form a ring; and R^9 , R^{10} , R^{11} and R^{12} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or a
 functional group, provided that any two of R^9 , R^{10} , R^{11} and R^{12} vicinal to one another may form a ring. Preferred groups for
 10 R^{15} are (XII), (XV) wherein q is 2 and/or each R^{16} is hydrogen, (XV) in which q is 1, each R^{16} on the terminal carbon atoms is hydrogen, and both R^{16} groups on the middle carbon atom are methyl $[-H_2CC(CH_3)_2CH_2-]$, and (XII), with
 (XV) being especially preferred. It is also preferred that
 15 R^{15} contain at least two carbon atoms, and that each of the free valencies of R^{15} are to different carbon atoms.

In another especially preferred embodiment of (X) and (XI), R^{15} is (XII) or (XXIII) and the total compounds [when R^{15} is (XII)] are of the formulas



(I); and



(III)


In (I), (III), (X), (XI), (XII), as appropriate it is preferred that:

R^1 , R^2 , R^3 and R^4 are each independently alkyl or silyl, more preferably alkyl containing 1 to 6 carbon atoms; and/or R^1 , R^2 , R^3 and R^4 are all the same; and/or R^5 , R^6 , R^7 and R^8 are each independently hydrogen or alkyl, more preferably all are hydrogen; and/or R^9 , R^{10} , R^{11} and R^{12} are all hydrogen; and/or one or more of R^9 , R^{10} , R^{11} and R^{12} are alkyl, aryl or substituted aryl.

In compounds such as (I) and (X) preferred transition metals are Zr, Ti, V and Hf, and Zr and Ti are more preferred. Preferred metal oxidation states are Ti[II, III, and IV], Zr[II and IV], Hf[IV], V[IV and V], Cr[III], Sc[III], Y[III] and the rare earth metals[III]. When lower oxidation states of the metals are employed, it may be beneficial to include an oxidant in the catalyst activation step. This may be an alkyl halide to provide simultaneous alkylation if the compound is not prealkylated, or a standard oxidant such as oxygen when another alkylating agent is used. In compounds in which silyl groups are present it is preferred that R^{16} , R^{17} and R^{18} are each independently alkyl or aryl, more preferably alkyl, and especially preferably all are methyl.

Anions X may have one negative charge (monoanion), or more than one negative charge (dianion, etc.). The number of anions, X, which corresponds to n, can be a fractional number or a whole number, depending on the number of residual positive charges on the ligand plus metal cation. For example if the metal valence is 3, and the anion is a dianion (X^{-2}), then n would be 0.5. Preferred anions are monoanions. Useful anions include acyl, alkoxide, hydride, halide, carboxylate, alkyl such as methyl, benzyl, neopentyl, neophyl, and trimethylsilylmethyl, and preferred anions are halide, especially chloride and bromide, and alkyl.

Included within the meaning of a compound of formula (I) are compounds of the formula



wherein R^1 through R^{12} , M, X and n are as described above and Z is a monovalent anion. This is simply a representation of (I) in which one of the anions X is not "bound" to the metal cation. Usually Z is a relatively noncoordinating anion.

Useful olefins for polymerization include one or more of ethylene, propylene, 1-butene, 1-hexene, 1-octene, styrene, norbornene, other α -olefins, cyclopentene and alkyl substituted cyclopentenenes. Copolymers, such as copolymers of ethylene and one or more α -olefins may also be made. Preferred olefins are one or more of ethylene, propylene and a linear α -olefin.

The second compound in the first polymerization process (and also useful in the second polymerization process), W, is a neutral Lewis acid that can abstract X^- from (I) or (X) to form WX^- . Useful Lewis acids for this abstraction include $B(C_6F_5)_3$, $AlCl_3$, $MgCl_2$ and alkyl aluminum compounds such as methyl aluminoxane, diethylaluminum chloride and ethylaluminum chloride. If a hydrocarbyl anion, preferably an alkyl anion, more preferably a methyl anion, or a hydride anion, is not bound to the metal atom of (I), W (or another W) must also transfer a hydrocarbyl (preferably an alkyl) or hydride anion to the metal atom. Essentially the same effect can be obtained by using one molecule of the alkyl aluminum compound to place an alkyl group on the metal, and another molecule to abstract the X anion. Preferred neutral Lewis acids for transferring a hydrocarbyl group to the metal atom are alkyl aluminum compounds. Suitable alkyl aluminum compounds include alkyl aluminum sesquioxides $[(R^{18}AlO)_n]$, especially wherein R^{18} is methyl. Alkyl aluminum sesquioxides are preferred alkyl aluminum compounds. W can also constitute a mixture of two compounds, a strong Lewis

acid such as $B(C_6F_5)_3$ and an alkylating agent such as triethylaluminum. A stoichiometric or larger amount of the neutral Lewis acid is preferred, and a more preferred molar ratio of W:(I) is about 1 to about 10,000, preferably about 10 to about 5,000.

In the first and second polymerization processes herein, the temperature at which the polymerization is carried out is about $-50^\circ C$ to about $+250^\circ C$, preferably about $-60^\circ C$ to about $150^\circ C$, more preferably about $-20^\circ C$ to about $100^\circ C$. The pressure of the olefin (if it is a gas) at which the polymerization is carried out is not critical, atmospheric pressure to about 275 MPa being a suitable range.

The polymerization processes herein may be run in the presence of various liquids, particularly aprotic organic liquids. The catalyst system, olefin, and polymer may be soluble or insoluble in these liquids, but obviously these liquids should not prevent the polymerization from occurring. Suitable liquids include alkanes, cycloalkanes, selected halogenated hydrocarbons, and aromatic hydrocarbons. Specific useful solvents include hexane, toluene, benzene methylene chloride, and 1,2,4-trichlorobenzene.

The olefin polymerizations herein may also initially be carried out in the solid state by, for instance, supporting the transition metal compound on a substrate such as silica or alumina, activating it with the Lewis (such as W, for instance an alkylaluminum compound) or Bronsted acid and exposing it to the olefin. Alternatively, the support may first be contacted (reacted) with W such as an alkylaluminum compound, and then contacted with an appropriate transition metal compound such as (I) or (X). The support may also be able to take the place of the Lewis or Bronsted acid, for instance an acidic clay such as montmorillonite. Another method of making a supported catalyst is to start a polymerization or at least make a transition metal complex of another olefin or oligomer of an olefin such as cyclopentene on a support such as silica or alumina. These "heterogeneous" catalysts may be used to catalyze polymerization in the gas phase or the liquid phase. By gas

phase is meant that a gaseous olefin is transported to contact with the catalyst particle.

In all of the polymerization processes described herein oligomers and polymers of the various olefins are made. They
5 may range in molecular weight from oligomeric olefins, to lower molecular weight oils and waxes, to higher molecular weight polyolefins. One preferred product is a polymer with a degree of polymerization (DP) of about 10 or more, preferably about 40 or more. By "DP" is meant the average
10 number of repeat (monomer) units in a polymer molecule.

Depending on its properties, the polymer made by the processes described herein is useful in many ways. For instance if it is a thermoplastic, it may be used as a molding resin, for extrusion, film, etc. If it is
15 elastomeric, it may be used as an elastomer.

Polyolefins are most often prepared by polymerization processes in which a transition metal containing catalyst system is used. Depending on the process conditions used and the catalyst system chosen, polymers, even those made from
20 the same monomer(s) may have varying properties. Some of the properties which may change are molecular weight and molecular weight distribution, crystallinity, melting point, and glass transition temperature. Except for molecular weight and molecular weight distribution, branching can
25 affect all the other properties mentioned.

It is known that certain transition metal containing polymerization catalysts including those disclosed herein, are especially useful in varying the branching in polyolefins made with them, see for instance World Patent Applications
30 96/23010, 97/02298, 98/30609 and 98/30610. It is also known that blends of distinct polymers, that vary for instance in the properties listed above, may have advantageous properties compared to "single" polymers. For instance it is known that polymers with broad or bimodal molecular weight distributions
35 may be melt processed (be shaped) more easily than narrower molecular weight distribution polymers. Similarly, thermoplastics such as crystalline polymers may often be toughened by blending with elastomeric polymers.

Therefore, methods of producing polymers which inherently produce polymer blends are useful especially if a later separate (and expensive) polymer mixing step can be avoided. However in such polymerizations one should be aware that two different catalysts may interfere with one another, or interact in such a way as to give a single polymer.

In such a process the catalysts disclosed herein can be termed the first active polymerization catalyst. Monomers useful with these catalysts are those described (and also preferred) above.

A second active polymerization catalyst (and optionally one or more others) is used in conjunction with the first active polymerization catalyst. The second active polymerization catalyst may be a late transition metal catalyst, for example as described in World Patent Applications 96/23010, 97/02298, 98/27124, 98/30609, 98/30610 and 98/30612. Other types of catalysts may also be used for the second active polymerization catalyst. For instance so-called Ziegler-Natta and/or metallocene-type catalysts may also be used. These types of catalysts are well known in the polyolefin field, see for instance Angew. Chem., Int. Ed. Engl., vol. 34, p. 1143-1170 (1995), European Patent Application 416,815 and U.S. Patent 5,198,401 for information about metallocene-type catalysts, and J. Boor Jr., Ziegler-Natta Catalysts and Polymerizations, Academic Press, New York, 1979 for information about Ziegler-Natta-type catalysts, all of which are hereby included by reference. Many of the useful polymerization conditions for all of these types of catalysts and the first active polymerization catalysts coincide, so conditions for the polymerizations with (I) or (X) are easily accessible. Oftentimes the "co-catalyst" or "activator" is needed for metallocene or Ziegler-Natta-type polymerizations. In many instances the same compound, such as an alkylaluminum compound, may be used as an "activator" for some or all of these various polymerization catalysts.

In one preferred process described herein the first olefin(s) [the monomer(s) polymerized by the first active

polymerization catalyst] and second olefin(s) [the monomer(s) polymerized by the second active polymerization catalyst] are identical, and preferred olefins in such a process are the same as described immediately above. The first and/or second
5 olefins may also be a single olefin or a mixture of olefins to make a copolymer. Again it is preferred that they be identical particularly in a process in which polymerization by the first and second active polymerization catalysts make polymer simultaneously.

10 In some processes herein the first active polymerization catalyst may polymerize a monomer that may not be polymerized by said second active polymerization catalyst, and/or vice versa. In that instance two chemically distinct polymers may be produced. In another scenario two monomers would be
15 present, with one polymerization catalyst producing a copolymer, and the other polymerization catalyst producing a homopolymer, or two copolymers may be produced which vary in the molar proportion or repeat units from the various monomers. Other analogous combinations will be evident to
20 the artisan.

In another variation of this process one of the polymerization catalysts makes an oligomer of an olefin, preferably ethylene, which oligomer has the formula $R^{70}CH=CH_2$, wherein R^{70} is n-alkyl, preferably with an even
25 number of carbon atoms. The other polymerization catalyst in the process then (co)polymerizes this olefin, either by itself or preferably with at least one other olefin, preferably ethylene, to form a branched polyolefin. Preparation of the oligomer (which is sometimes called an α -olefin) by a second active polymerization-type of catalyst
30 can be found in World Patent Applications 96/23010 and 98/30612.

Likewise, conditions for such polymerizations, using catalysts of the second active polymerization type, will also
35 be found in the appropriate above mentioned references.

Two chemically different active polymerization catalysts are used in this polymerization process. The first active polymerization catalyst is described in detail above. The

second active polymerization catalyst may also meet the limitations of the first active polymerization catalyst, but must be chemically distinct. For instance, it may have a different transition metal present, and/or utilize a different type of ligand and/or the same type of ligand which differs in structure between the first and second active polymerization catalysts. In one preferred process, the ligand type and the metal are the same, but the ligands differ in their substituents.

Included within the definition of two active polymerization catalysts are systems in which a single polymerization catalyst is added together with another ligand, preferably the same type of ligand, which can displace the original ligand coordinated to the metal of the original active polymerization catalyst, to produce in situ two different polymerization catalysts.

The molar ratio of the first active polymerization catalyst to the second active polymerization catalyst used will depend on the ratio of polymer from each catalyst desired, and the relative rate of polymerization of each catalyst under the process conditions. For instance, if one wanted to prepare a "toughened" thermoplastic polyethylene that contained 80% crystalline polyethylene and 20% rubbery polyethylene, and the rates of polymerization of the two catalysts were equal, then one would use a 4:1 molar ratio of the catalyst that gave crystalline polyethylene to the catalyst that gave rubbery polyethylene. More than two active polymerization catalysts may also be used if the desired product is to contain more than two different types of polymer.

The polymers made by the first active polymerization catalyst and the second active polymerization catalyst may be made in sequence, i.e., a polymerization with one (either first or second) of the catalysts followed by a polymerization with the other catalyst, as by using two polymerization vessels in series. However it is preferred to carry out the polymerization using the first and second active polymerization catalysts in the same vessel(s), i.e.,

simultaneously. This is possible because in most instances the first and second active polymerization catalysts are compatible with each other, and they produce their distinctive polymers in the other catalyst's presence. Any of the processes applicable to the individual catalysts may be used in this polymerization process with 2 or more catalysts, i.e., gas phase, liquid phase, continuous, etc.

The polymers produced by this process may vary in molecular weight and/or molecular weight distribution and/or melting point and/or level of crystallinity, and/or glass transition temperature and/or other factors. For copolymers the polymers may differ in ratios of comonomers if the different polymerization catalysts polymerize the monomers present at different relative rates. The polymers produced are useful as molding and extrusion resins and in films as for packaging. They may have advantages such as improved melt processing, toughness and improved low temperature properties.

Hydrogen may be used to lower the molecular weight of polyolefin produced in the first or second processes. It is preferred that the amount of hydrogen present be about 0.01 to about 50 mole percent of the olefin present, preferably about 1 to about 20 mole percent. When liquid monomers (olefins) are present, one may need to experiment briefly to find the relative amounts of liquid monomers and hydrogen (as a gas). If both the hydrogen and monomer(s) are gaseous, their relative concentrations may be regulated by their partial pressures.

In the Examples, the following abbreviations are used:

ΔH_f - heat of fusion (of polymer)

Cy - cyclohexyl

GPC - Gel Permeation Chromatography

MI - melt index

Mn - number average molecular weight

Mw - weight average molecular weight

PE - polyethylene

PMAO - poly(methylaluminoxane)

PMAO-IP - see PMAO

PP - polypropylene
Pr - propyl
RT - room temperature
THF - tetrahydrofuran

5 In the Examples, all pressures are gauge pressures.

"Me/1000 CH₂" is the total number of methyl groups per 1000 methylene groups in the polymer and is measured by ¹H NMR. For method of NMR measurement and calculations, see World Patent Application 96/23010.

10 Differential Scanning Calorimetry was used to measure polymer melting points (T_m in °C, taken as the peak of the melting endotherm), and heat of fusion (ΔH_f in J/g), using a heating rate of 10°C/min. Results reported are from the second heat.

15 The dimagnesium reagents were prepared according to the procedure of M. F. Lappert and T. R. Martin, J. Chem. Soc. Dalton Trans. **1982**, 1959. Excess magnesium metal was reacted with dichloro- or dibromo-hydrocarbon compounds in THF at RT to yield a high yield of the dimagnesium reagents which were
20 then reacted with 1 equiv of the carbodiimide in THF at RT for 2-3 days. The solvent was removed in vacuo and the crude products were washed with pentane to give a white powder product.

25

Example 1

Synthesis of [MgCl]₂[(i-PrN)₂CCH₂C₆H₄-o-CH₂C(NPr-i)₂]

In a dry-box, to a solution of [MgCl]₂[CH₂C₆H₄-o-CH₂] (0.0164 mol) in THF at -30°C was added dropwise a solution of 1,3-diisopropylcarbodiimide (4.139 g, 0.0327 mol) in THF.
30 The pale yellow reaction mixture was stirred 2 days. The solvent was removed in vacuo and the white sticky crude product was washed with pentane to give a white powder product (5.1558 g, 0.0108 mol) in 66% yield. ¹H NMR (CD₂Cl₂): 1.31 (m, 24H, CH₃), 3.1 (s, 4H, CH₂), 3.58 (m, 4H, i-Pr-CH),
35 7.22 (m, 2H, Ar-H), 7.58 (m, 2H, Ar-H).

Example 2

Synthesis of $[MgCl]_2[(NC_6H_{11})_2CCH_2C_6H_4-o-CH_2C(NC_6H_{11})_2]$

In a dry-box, to a solution of $[MgCl]_2[CH_2C_6H_4-o-CH_2]$ (0.0169 mol) in THF at $-30^\circ C$ was added dropwise a solution of 1,3-dicyclohexylcarbodiimide (6.971 g, 0.0338 mol) in THF. The pale yellow reaction mixture was stirred 3 days. The solvent was removed in vacuo and the white sticky crude product was washed with pentane to give a white powder product (7.698 g, 0.0121 mol) in 72% yield. 1H NMR (CD_2Cl_2): broad, 1.0 - 1.8 (m, 20H, Cy- CH_2), 3.0 (m, 4H, Cy-CH), 3.69 (br, 2H, CH_2), 3.78 (br, 2H, CH_2), 7.2 (m, Ar-H).

Example 3

Synthesis of $[MgBr]_2[(i-PrN)_2CCH_2CH_2CH_2CH_2C(NPr-i)_2]$

The general procedure was followed using 11.25 mmol of $[MgBr]_2[CH_2CH_2CH_2CH_2]$ and 2.8395 g (22.5 mmol) of 1,3-diisopropylcarbodiimide. A white powder product (6.3672 g, 8.72 mmol) was isolated in 78% yield. 1H NMR (CD_2Cl_2): 1.08 (d, 24H, CH_3), 1.57 (br, 4H, CH_2), 1.90 (m, THF coordinated CH_2), 2.29 (br, 4H, CH_2), 3.54 (br, 4H, CH), 3.80 (m, THF coordinated OCH_2).

Example 4

Synthesis of $[MgBr]_2[(ArN)_2CCH_2CH_2CH_2CH_2C(NAr)_2]$: [Ar = 2,6-(i-Pr) $_2C_6H_3$]

The general procedure was followed using 15.6 mmol of $[MgBr]_2[CH_2CH_2CH_2CH_2]$ and 11.3354 g (31.2 mmol) of 1,3-bis[2,6-diisopropylphenyl]carbodiimide. A white powder product (15.9027 g, 12.1 mmol) was isolated in 78% yield. 1H NMR (CD_2Cl_2): 0.35 (br, 4H, CH_2), 0.86 (d, 24H, CH_3), 0.96 (d, 24H, CH_3), 1.19 (br, 4H, CH_2), 1.70 (m, THF coordinated CH_2), 3.08 (br, 8H, CH), 3.70 (m, THF coordinated OCH_2), 6.83 (m, 12H, Ar-H).

Example 5

Synthesis of $[\text{MgCl}]_2[(\text{ArN})_2\text{CCH}_2(\text{C}_6\text{H}_4)-m\text{-CH}_2\text{C}(\text{NAr})_2]$: [Ar = 2,6-(i-Pr) $_2\text{C}_6\text{H}_3]$

The general procedure was followed using 37.0 mmol of
 5 $[\text{MgCl}]_2[\text{CH}_2\text{C}_6\text{H}_4-m\text{-CH}_2]$ and 26.8294 g (74.0 mmol) of 1,3-bis[2,6-diisopropylphenyl]carbodiimide. A pale yellow powder product (36.34 g, 28.26 mmol) was isolated in 76% yield. ^1H NMR (CD_2Cl_2): 0.35 (br, 4H, CH_2), 0.86 (d, 24H, CH_3), 0.96 (d, 24H, CH_3), 1.19 (br, 4H, CH_2), 1.70 (m, THF coordinated CH_2), 3.08 (br, 8H, CH), 3.70 (m, THF coordinated OCH_2), 6.83 (m, 12H, Ar-H).

Example 6

Synthesis of $[\text{MgCl}]_2[(i\text{-PrN})_2\text{CCH}_2(\text{C}_6\text{H}_4)-m\text{-CH}_2\text{C}(\text{NPr-}i)_2]$

15 The general procedure was followed using 14.7 mmol of $[\text{MgCl}]_2[\text{CH}_2\text{C}_6\text{H}_4-m\text{-CH}_2]$ and 3.7021 g (29.34 mmol) of 1,3-diisopropylcarbodiimide. A white powder product (4.675 g, 7.37 mmol) was isolated in 50% yield. ^1H NMR (CD_2Cl_2): 0.79 (d, 24H, CH_3), 1.73 (m, 4H, THF coordinated CH_2), 3.2 (m, 4H, CH), 3.48 (s, 4H, CH_2), 3.82 (m, 4H, THF coordinated OCH_2), 6.85 (m, 2H, Ar-H), 6.96 (m, 2H, Ar-H).

Example 7

25 Synthesis of $[\text{MgBr}]_2[(\text{ArN})_2\text{CCH}_2\text{CH}_2\text{CH}_2\text{CH}_2\text{C}(\text{NAr})_2]$: [Ar = 4-Me- C_6H_4]

The general procedure was followed using 9.42 mmol of $[\text{MgBr}]_2[\text{CH}_2\text{CH}_2\text{CH}_2\text{CH}_2]$ and 4.19 g (18.85 mmol) of 1,3-bis[4-methylphenyl]carbodiimide. A white powder product (7.4264 g, 7.57 mmol) was isolated in 80% yield. ^1H NMR (CD_2Cl_2): 1.20 (br, 2 x CH_2 and THF overlap), 2.21 (s, 12H, CH_3), 2.32 (br, 4H, CH_2), 3.70 (br, THF coordinated OCH_2), 6.65 - 7.22 (m, 16H, Ar-H).

Example 8


35 Synthesis of $[\text{MgCl}]_2[(\text{ArN})_2\text{CCH}_2(\text{C}_6\text{H}_4)-m\text{-CH}_2\text{C}(\text{NAr})_2]$: [Ar = 4-Me- $\text{C}_6\text{H}_4]$

The general procedure was followed using 9.17 mmol of $[\text{MgCl}]_2[\text{CH}_2\text{C}_6\text{H}_4-m\text{-CH}_2]$ and 4.077 g (18.34 mmol) of 1,3-bis[4-


methylphenyl]carbodiimide. A pale yellow powder product (7.0 g, 7.16 mmol) was isolated in 78% yield. ^1H NMR (CD_2Cl_2): 1.28 (br, THF- CH_2), 2.22 (s, 12H, CH_3), 3.70 (br, THF coordinated OCH_2), 4.05 (s, 4H, CH_2), 6.65 - 7.15 (m, 16H, Ar-H).

General Procedure for Synthesis of Transition Metal Complexes of Bis-(carboximidatonate)


A flask containing a suspension of metal halide in pentane or methylene chloride or toluene was cooled at -30°C in the dry-box freezer. To this was added dropwise a pre-cooled solution of bis-(carboximidatonate) dimagnesium reagent in CH_2Cl_2 . The reaction mixture was stirred overnight at RT and filtered through a frit with dry Celite. The solvent was removed under vacuo and the residue was extracted with methylene chloride. Removed methylene chloride and washed with pentane and then dried in vacuo to give the early-transition metal complexes. The formulas below list the catalysts synthesized in these examples.




1: M = Ti,
2: M = Zr,
3: M = Hf.



4: M = Ti,
5: M = Zr,
6: M = Hf.




7: M = Ti,
8: M = Zr,
9: M = Hf.



Ar = 2,6-*i*-Pr-C₆H₄

10: M = Ti,
11: M = Zr,
12: M = Hf,
13: M = V (III) *,
14: M = Y *,
15: M = Cr (III) *.




Ar = 2,6-*i*-Pr-C₆H₄

16: M = Ti,
17: M = Zr,
18: M = Hf.

Ar = 4-Me-C₆H₄

23: M = Ti,
24: M = Zr.



19: M = Ti,
20: M = Zr.

Ar = 4-Me-C₆H₄

21: M = Ti,
22: M = Zr.

* One Cl atom on the metal.

Example 9

Synthesis of [(*i*-PrN)₂CCH₂C₆H₄-*o*-CH₂C(NPr-*i*)₂]TiCl₂: 1

5 In a dry-box, a solution of [MgCl]₂[(*i*-PrN)₂CCH₂C₆H₄-*o*-CH₂C(NPr-*i*)₂] (1.299 mmol) in toluene (14 mL) and THF (1 mL) was added dropwise to a pre-cooled solution of TiCl₄ (0.2464 g, 1.299 mmol) in toluene at -30°C. The purple reaction mixture was stirred 2 days and the solvent was removed in vacuo. The residue was extracted with methylene chloride. After removal of the solvent, a dark purple powder was obtained, 0.5215 g (1.097 mmol) in 84% yield. ¹H NMR (CD₂Cl₂): contain different isomers. 1.06 - 1.30 (br., m, 24H, CH₃), 2.62 - 2.96 (s, 4H, CH₂), 3.26 - 3.72 (m, 4H, *i*-Pr-CH), 6.86 - 7.30 (br., m, 4H, Ar-H).

Example 10Synthesis of $[(i\text{-PrN})_2\text{CCH}_2\text{C}_6\text{H}_4\text{-o-CH}_2\text{C(NPr-i)}_2]\text{ZrCl}_2$: 2

In a dry-box, a solution of $[\text{MgCl}]_2[(i\text{-PrN})_2\text{CCH}_2\text{C}_6\text{H}_4\text{-o-CH}_2\text{C(NPr-i)}_2]$ (0.7716 mmol) in toluene (14 mL) and THF (1 mL) was dropwise added a pre-cooled suspension of ZrCl_4 (0.1798 g, 0.7716 mmol) in toluene at -30°C . The cloudy pale yellow reaction mixture was stirred 2 days and the solvent was removed in vacuo. The residue was extracted with methylene chloride. After removal of the solvent, a pale yellow powder was obtained, 0.1963 g (0.378 mmol) in 49% yield. ^1H NMR (CD_2Cl_2): contain different isomers. 0.96 - 1.35 (br., m, 24H, CH_3), 2.62 - 3.04 (s, 4H, CH_2), 3.18 - 3.78 (m, 4H, $i\text{-Pr-CH}$), 6.80 - 7.40 (br., m, 4H, Ar-H).

Example 11Synthesis of $[(i\text{-PrN})_2\text{CCH}_2\text{C}_6\text{H}_4\text{-o-CH}_2\text{C(NPr-i)}_2]\text{HfCl}_2$: 3

The general procedure for metal complexes was followed using 0.3943 g (0.835 mmol) of the dimagnesium reagent and 0.2673 g (0.835 mmol) of HfCl_4 and methylene chloride as solvent. A pale yellow solid (0.3002 g, 0.495 mmol) was obtained in 59% yield. ^1H NMR spectrum in CD_2Cl_2 is complex and similar to the Zr analog compound.

Example 12Synthesis of $[(\text{NC}_6\text{H}_{11})_2\text{CCH}_2\text{C}_6\text{H}_4\text{-o-CH}_2\text{C(NC}_6\text{H}_{11})_2]\text{TiCl}_2$: 4

The general procedure for metal complexes was followed using 0.7168 g (1.126 mmol) of the dimagnesium reagent and 0.2137 g (1.126 mmol) of TiCl_4 . A purple solid (0.4335 g, 0.682 mmol) was obtained in 61% yield. The ^1H NMR spectrum in CD_2Cl_2 is complex.

Example 13Synthesis of $[(\text{NC}_6\text{H}_{11})_2\text{CCH}_2\text{C}_6\text{H}_4\text{-o-CH}_2\text{C(NC}_6\text{H}_{11})_2]\text{ZrCl}_2$: 5

The general procedure for metal complexes was followed using 0.6267g (0.9848 mmol) of the dimagnesium reagent and 0.2295 g (0.9848 mmol) of ZrCl_4 . A pale yellow solid (0.2817 g, 0.415 mmol) was obtained in 42% yield. The ^1H NMR spectrum in CD_2Cl_2 is complex.

Example 14Synthesis of $[(NC_6H_{11})_2CCH_2C_6H_4-o-CH_2C(NC_6H_{11})_2]HfCl_2$: 6

The general procedure for metal complexes was followed using 0.4603g (0.723 mmol) of the dimagnesium reagent and 0.2317 g (0.723 mmol) of $ZrCl_4$. A pale yellow solid (0.4742 g, 0.619 mmol) was obtained in 86% yield. The 1H NMR spectrum in CD_2Cl_2 is complex and similar to the Zr analog compound.

Example 15Synthesis of $[(i-PrN)_2CCH_2CH_2CH_2CH_2C(NPr-i)_2]TiCl_2$: 7

The general procedure for metal complexes was followed using 0.8054g (1.104 mmol) of the dimagnesium reagent and 0.2094 g (1.104 mmol) of $TiCl_4$. A dark red solid (0.6485 g, 0.906 mmol) was obtained in 82% yield. The 1H NMR spectrum in CD_2Cl_2 is complex and similar to the Zr analog compound.

Example 16Synthesis of $[(i-PrN)_2CCH_2CH_2CH_2CH_2C(NPr-i)_2]ZrCl_2$: 8

The general procedure for metal complexes was followed using 0.7443 g (1.02 mmol) of the dimagnesium reagent and 0.2377 g (1.02 mmol) of $ZrCl_4$. A pale yellow solid (0.5660 g, 0.735 mmol) was obtained in 72% yield. 1H NMR (CD_2Cl_2) 1.25 (br., m, 24H, CH_3), 1.58 (s, 4H, CH_2), 1.87 (m, 4H, THF- CH_2), 2.38 (s, 4H, CH_2), 3.60 (m, 4H, $i-Pr-CH$), 3.94 (m, 4H, OCH_2).

Example 17Synthesis of $[(i-PrN)_2CCH_2CH_2CH_2CH_2C(NPr-i)_2]HfCl_2$: 9

The general procedure for metal complexes was followed using 0.4647g (0.6369 mmol) of the dimagnesium reagent and 0.2040 g (0.6369 mmol) of $HfCl_4$. A pale yellow solid (0.15 g, 0.269 mmol) was obtained in 42% yield. 1H NMR (CD_2Cl_2) 1.21 (br., m, 24H, CH_3), 1.60 (s, 4H, CH_2), 1.92 (m, 4H, THF- CH_2), 2.40 (s, 4H, CH_2), 3.78 (m, 4H, $i-Pr-CH$), 4.0 (m, 4H, OCH_2).

Example 18Synthesis of {[N(2,6-i-Pr₂-C₆H₃)]₂CCH₂CH₂CH₂CH₂C[N(2,6-i-Pr₂-C₆H₃)]₂}TiCl₂: 10

The general procedure for metal complexes was followed using 2.6268 g (2.0 mmol) of the dimagnesium reagent and 0.3792 g (2.0 mmol) of TiCl₄. A red solid (2.1 g, 2.0 mmol) was obtained in ~100% yield. ¹H NMR (CD₂Cl₂): 0.75-1.35 (m, overlap peaks, 56H, CH₂ and CH₃), 1.80 (m, THF coordinated CH₂), 2.92 (br, 2H, CH), 2.98 (br, 4H, CH), 3.14 (br, 2H, CH), 3.88 (m, THF coordinated OCH₂), 6.75-7.30 (m, 12H, Ar-H).

Example 19Synthesis of {[N(2,6-i-Pr₂-C₆H₃)]₂CCH₂CH₂CH₂CH₂C[N(2,6-i-Pr₂-C₆H₃)]₂}ZrCl₂: 11

The general procedure for metal complexes was followed using 2.7864 g (2.12 mmol) of the dimagnesium reagent and 0.4941 g (2.12 mmol) of ZrCl₄. An off-white solid (1.45 g, 1.54 mmol) was obtained in 73% yield. ¹H NMR (CD₂Cl₂): 1.08 (d, 12H, CH₃), 1.15 (d, 12H, CH₃), 1.33 (d, 12H, CH₃), 1.40 (d, 12H, CH₃), 1.25 (br, 4H, CH₂), 1.92 (br, 4H, CH₂), 1.92 (m, THF coordinated CH₂), 2.75 (br, 4H, CH), 3.04 (br, 4H, CH), 3.94 (m, THF coordinated OCH₂), 6.90-7.68 (m, 12H, Ar-H).

Example 20Synthesis of {[N(2,6-i-Pr₂-C₆H₃)]₂CCH₂CH₂CH₂CH₂C[N(2,6-i-Pr₂-C₆H₃)]₂}HfCl₂: 12

The general procedure for metal complexes was followed using 2.3058 g (1.75 mmol) of the dimagnesium reagent and 0.5620 g (1.75 mmol) of HfCl₄. An off-white solid (1.60 g, 1.55 mmol) was obtained in 89% yield. ¹H NMR (CD₂Cl₂): 0.32 (br, 4H, CH₂), 0.84 (d, 24H, CH₃), 0.98 (d, 24H, CH₃), 1.82 (m, THF coordinated CH₂), 1.92 (br, 4H, CH₂), 2.88 (br, 4H, CH), 3.08 (br, 4H, CH), 3.88 (m, THF coordinated OCH₂), 6.72-7.20 (m, 12H, Ar-H).

Example 21

Synthesis of {[N(2,6-i-Pr₂-C₆H₃)]₂CCH₂CH₂CH₂CH₂C[N(2,6-i-Pr₂-C₆H₃)]₂}VCl: 13

The general procedure for metal complexes was followed using 0.3910 g (0.3 mmol) of the dimagnesium reagent and 0.0468 g (0.3 mmol) of VCl₃. A purple solid which is not soluble in any organic solvents was received.

Example 22

Synthesis of {[N(2,6-i-Pr₂-C₆H₃)]₂CCH₂CH₂CH₂CH₂C[N(2,6-i-Pr₂-C₆H₃)]₂}YCl: 14

The general procedure for metal complexes was followed using 0.5633 g (0.43 mmol) of the dimagnesium reagent and 0.0837 g (0.43 mmol) of YCl₃. An off-white solid (0.4 g, 0.41 mmol) was obtained in 94% yield. ¹H NMR (CD₂Cl₂): complex.

Example 23

Synthesis of {[N(2,6-i-Pr₂-C₆H₃)]₂CCH₂CH₂CH₂CH₂C[N(2,6-i-Pr₂-C₆H₃)]₂}CrCl: 15

The general procedure for metal complexes was followed using 0.2939 g (0.22 mmol) of the dimagnesium reagent and 0.0838 g (0.22 mmol) of CrCl₃·3THF. A pale green solid was obtained. ¹H NMR (CD₂Cl₂): 1.08 (d, 12H, CH₃), 1.28 (d, 12H, CH₃), 1.50 (m, 24H, CH₃), 2.15 (br, 4H, CH₂), 2.22 (br, 4H, CH₂), 3.36 (m, 4H, CH), 3.46 (br, 4H, CH), 6.92 - 7.45 (m, 12H, Ar-H).

Example 24

Synthesis of {[N(2,6-i-Pr₂-C₆H₃)]₂CCH₂C₆H₄-m-CH₂C[N(2,6-i-Pr₂-C₆H₃)]₂}TiCl₂: 16

The general procedure for metal complexes was followed using 1.5927 g (1.239 mmol) of the dimagnesium reagent and 0.2350 g (1.24 mmol) of TiCl₄. A red brown solid (1.18 g, 1.2 mmol) was obtained in 97% yield. ¹H NMR (CD₂Cl₂): complex and contained different isomers.

Example 25Synthesis of {[N(2,6-*i*-Pr₂-C₆H₃)]₂CCH₂C₆H₄-*m*-CH₂C[N(2,6-*i*-Pr₂-C₆H₃)]₂}ZrCl₂: 17

The general procedure for metal complexes was followed using 1.3342 g (1.038 mmol) of the dimagnesium reagent and 0.2418 g (1.038 mmol) of ZrCl₄. A pale yellow solid (1.05 g, 1.1 mmol) was obtained in ~100% yield. ¹H NMR (CD₂Cl₂): complex and contained different isomers.

Example 26Synthesis of {[N(2,6-*i*-Pr₂-C₆H₃)]₂CCH₂C₆H₄-*m*-CH₂C[N(2,6-*i*-Pr₂-C₆H₃)]₂}HfCl₂: 18

The general procedure for metal complexes was followed using 1.4227 g (1.106 mmol) of the dimagnesium reagent and 0.3544 g (1.106 mmol) of HfCl₄. A pale yellow solid (0.9741 g) was obtained. The pale yellow solid was extracted with pentane. The pentane solution was concentrated and cooled in the freezer to yield colorless crystals which was identified as neutral ligand (identified by x-ray crystal structure). It is believed that trace of HCl contaminated in HfCl₄ reacted with the dimagnesium reagent to form the neutral ligand as a low-level byproduct.

Example 27Synthesis of [N(*i*-Pr)]₂CCH₂C₆H₄-*m*-CH₂C[N(*i*-Pr)]₂}TiCl₂: 19

At -30°C in the dry-box, to a solution of 0.2805 g (0.84 mmol) of TiCl₄(THF)₂ in 30 mL of toluene, was slowly added a solution 0.84 mmol of the dimagnesium reagent in 20 mL of toluene. The dark red reaction mixture was stirred overnight at RT and filtered through a Celite® plug frit. After removing the solvent and rinsing with pentane, a dark red solid was obtained, 0.21 g, 0.44 mmol in 53% yield. ¹H NMR (CD₂Cl₂): 1.4 (br, 24H, CH₃), 3.92 (br, 8H, CH₂ and CH-Pr-*i*), 7.12 - 7.4 (m, 4H, Ar-H).

Example 28Synthesis of $[N(i\text{-Pr})]_2CCH_2C_6H_4\text{-}m\text{-}CH_2C[N(i\text{-Pr})]_2ZrCl_2$: 20

At -30°C , in a dry-box, to a solution of 0.3169 g (0.84 mmol) of $ZrCl_4(THF)_2$ in 30 mL of toluene was slowly added a solution of 0.84 mmol of the dimagnesium reagent in 20 mL of toluene. The cloudy reaction mixture was stirred overnight at RT and filtered through a Celite plug frit. After removing the solvent and rinsing with pentane, a pale yellow solid was obtained, 0.34 g, 0.65 mmol in 78% yield. ^1H NMR (CD_2Cl_2): 1.42 (br, 24H, CH_3), 3.88 (br, 4H, $CH\text{-}Pr\text{-}i$), 4.05 (s, 4H, CH_2), 7.25 - 7.54 (m, 4H, Ar-H).

Example 29Synthesis of $\{[N(4\text{-Me-C}_6\text{H}_4)]_2CCH_2CH_2CH_2CH_2C[N(4\text{-Me-C}_6\text{H}_4)]_2\}TiCl_2$: 21

At -30°C , in a dry-box to a solution of 0.1564 g (0.47 mmol) of $TiCl_4(THF)_2$ in 30 mL of toluene, was slowly added a solution of 0.47 mmol of the dimagnesium reagent in 20 mL of toluene. The red reaction mixture was stirred overnight at RT and filtered through a Celite® plug frit. After removing the solvent and rinsing with pentane, a red solid was obtained, 0.33 g, 0.53 mmol in ~100% yield. ^1H NMR (CD_2Cl_2): contains toluene and coordinate THF. 0.53 (br, 4H, CH_2), 1.58 (s, 4H, CH_3), 1.72 (br, THF- CH_2), 2.18 (br, 12H, CH_3), 3.78 (br, THF- OCH_2), 6.31 - 7.12 (m, 16H, Ar-H).

Example 30 $\{[N(4\text{-Me-C}_6\text{H}_4)]_2CCH_2CH_2CH_2CH_2C[N(4\text{-Me-C}_6\text{H}_4)]_2\}ZrCl_2$: 22

At -30°C , in the dry-box, to a solution of 0.3791 g (1.63 mmol) of $ZrCl_4(THF)_2$ in 30 mL of toluene, was slowly added a solution of 1.63 mmol of the dimagnesium reagent in 20 mL of toluene. The pale yellow cloudy reaction mixture was stirred overnight at RT and filtered through a Celite plug frit. After removing the solvent and rinsing with pentane, a pale yellow solid was obtained, 1.06 g, 1.60 mmol in 98% yield. ^1H NMR (CD_2Cl_2): 0.60 (br, 4H, CH_2), 0.98 (br, 4H, CH_2), 1.36 (br, THF- CH_2), 2.20 (br, 12H, CH_3), 3.80 (br, THF- OCH_2), 6.08 - 6.95 (br, 16H, Ar-H).

Example 31Synthesis of {[N(4-Me-C₆H₄)]₂CCH₂C₆H₄-m-CH₂C[N(4-Me-C₆H₄)]₂}TiCl₂: 23

At -30°C, in the dry-box, to a solution of 0.1534 g (0.46 mmol) of TiCl₄(THF)₂ in 30 mL of toluene, was slowly added a solution of 0.4491 g (0.46 mmol) of the dimagnesium reagent in 20 mL of toluene. The red reaction mixture was stirred overnight at RT and filtered through a Celite plug frit. After removing the solvent and rinsing with pentane, a dark red solid was obtained, 0.30 g, 0.45 mmol in 98% yield. ¹H NMR (CD₂Cl₂): contains toluene. 1.96 (br, 12H, CH₃), 3.15 (br, 4H, CH₂), 6.64 - 7.00 (m, 20H, Ar-H).

Example 32Synthesis of {[N(4-Me-C₆H₄)]₂CCH₂C₆H₄-m-CH₂C[N(4-Me-C₆H₄)]₂}ZrCl₂: 24

At -30°C, in the dry-box, to a solution of 0.2417 g (1.037 mmol) of ZrCl₄(THF)₂ in 30 mL of toluene, was slowly added a solution of 1.014 g (1.037 mmol) of the dimagnesium reagent in 20 mL of toluene. The pale yellow cloudy reaction mixture was stirred overnight at RT and filtered through a Celite plug frit. After removing the solvent and rinsing with pentane, a pale yellow solid was obtained, 0.6 g, 0.84 mmol in 81% yield. ¹H NMR (CD₂Cl₂): contains toluene. 1.7 (br, THF-CH₂), 2.15 (br, 12H, CH₃), 3.70 (br, THF-OCH₂), 3.88 (br, 4H, CH₂), 6.24 - 7.00 (m, 20H, Ar-H).

Examples 33 - 45Polymerization of Ethylene at About 35 kPa

Method A: In a dry-box, 0.02 mmol of the bis(carboximidatone) transition metal catalyst was placed in a Schlenk flask and 35 mL of toluene was added to dissolve or partially dissolve the catalyst. The flask was sealed, removed from the dry-box and attached to an ethylene Schlenk line. After pumping off the air and nitrogen and purging with ethylene, 4.649 mL (20 mmol) of PMAO was quickly added to the flask under about 35 kPa ethylene. After being stirred at RT overnight, the reaction mixture was quenched with 50 mL

of a methanol solution of concentrated HCl (10% volume). The polymer was collected on a frit, washed with methanol and acetone thoroughly and then dried in vacuo overnight.

Method B: In the dry-box, 0.02 mmol of the bis(carboximidatone) transition metal catalyst was placed in a Schlenk flask containing 35 mL of toluene and 4.649 mL (20 mmol) of PMAO. The flask was sealed, removed from the dry-box and attached to an ethylene Schlenk line. After pumping off the air and nitrogen and purging with ethylene, the reaction mixture was stirred overnight at RT under about 35 kPa ethylene and then, quenched with 50 mL of a methanol solution of concentrated HCl (10% volume). The polymer was collected on a frit, washed with methanol and acetone thoroughly and then dried in vacuo overnight.

The polymers formed were linear high density PE, very high molecular weight and it was difficult get a GPC measurement. All the melt index tests showed no flow. The detailed data are listed in Table 1.

Table 1. Polymerization of Ethylene at 35 kPa

Example	Method	Catalyst	PE (g)	Productivity (mol PE/mol complex)	T _m (°C)	ΔH _f (J/g)	Me/1000CH ₂
33	A	1	3.0086	4512	132.5	128.5	1.5
34	A	2	1.1464	1547	134.65	121.9	7.7
35	A	3	0.0664	103	135.09	196.8	
36	A	4	4.6791	7417	132.27	148.7	
37	A	5	1.0688	1797	134.45	151.8	
38	A	6	0.0575	101	133.51	181.7	
39	B	7	3.4416	6026	134.7	109.5	
40 ^a	B	10	1.6214	5594	134.97	169.4	
41	B	11	1.5633	5975	134.78	174.8	
42	B	16	4.8137	5.42 x 10 ⁴	134.63	175.7	
43 ^b	B	16	12.002	1.35 x 10 ⁵	134.94	150.2	
44	B	19	0.3683	4458	134.49	173.4	
45	B	20	3.1324	2.41 x 10 ⁴	134.81	165.7	

Note: a. 0.01 mmol catalyst and 1 hr. reaction; b. 0.003 mmol catalyst and 18 hr. reaction.

Examples 46-65

Polymerization of ethylene at 6.9 MPa

In a dry-box, 0.002-0.01 mmol of the catalyst was placed in a glass vial and dissolved in 5 mL of 1,2,4-

trichlorobenzene. The vial was cooled to -30°C in the drybox freezer. PMAO was added to the vial on top of the frozen solution and the vial was then capped and sealed. Outside the drybox, the vials were placed into a shaker tube which was then shaken mechanically under high pressure ethylene for about 18 h. The white polymer was cut to pieces and added to a 100 mL of methanol solution of concentrated HCl (10 % volume). The mixture was stirred overnight and filtered. The polymer was collected on a frit, washed with acetone and dried in vacuo.

The polymers formed were linear (for example: $\text{Me}/1000\text{CH}_2$ for example 47 is 3.5) high density PE, very high molecular weight and it was difficult to get GPC measurements. All the melt index tests showed no flow. The detailed data are listed in Table 2.

Table 2. Polymerization of Ethylene at High Pressure C_2H_4

Example	Catalyst	PE (g)	Productivity (Mol PE / Mol complex.)	Pressure (MPa)	T_m ($^{\circ}\text{C}$)	ΔH_f (J/g)
46	1	9.3695	2.84×10^4	6.9	133.92	133.5
47	2	20.2679	6.35×10^4	6.9	137.01	164.5
48	3	2.1268	7293	3.5	137.48	160.8
49	5	5.46	1.74×10^4	3.5	136.04	146.2
50	6	3.6012	1.31×10^4	3.5	138.87	99.57
51	7	2.6388	9553	3.5	133.35	134.9
52	8	5.6004	2.02×10^4	3.5	135.86	204.5
53	9	10.3810	3.45×10^4	3.5	135.88	160.6
54	10	12.1552	3.71×10^4	3.5	131.69	147.6
55	11	8.9461	3.27×10^4	3.5	136.3	142.7
56	12	3.3109	1.13×10^4	3.5	137.25	124.5
57	14	0.0	0.0	3.5		
58	15	10.0044	3.44×10^4	3.5	134.86	158.1
59	16	2.298	3.38×10^4	3.5	135.97	118.9
60	17	5.6168	2.36×10^4	3.5	134.5	160.4
61	18	0.9013	5502	3.5	135.69	147.7
62	21	13.2227	3.65×10^4	1.4	132.76	171.9
63	23	7.7944	2.23×10^4	1.4	131.82	190.3
64	4	1.1221	3795	1.4	131.22	79.62
65	5	1.6998	5486	1.4	135.45	146.2

The detailed data of polymerization with catalyst 10 under mixture of H_2 and C_2H_4 are listed in Table 3.

Table 3. Polymerization of Ethylene under H_2/C_2H_4

Example	H_2 Pressure (kPa)	Total Pressure (MPa)	PE (g)	Productivity (mol PE/mol compound)	T_m ($^{\circ}C$)	ΔH_f (J/g)	MI
66	0	1.03	8.584	2.12×10^5	135.96	165.5	no flow
67	69	1.03	6.104	8.62×10^4	134.66	176.4	no flow
68	290	1.03	6.347	7.83×10^4	134.62	176.6	no flow
69a	610	1.03	9.774	1.31×10^5	132.96	184.0	no flow
70a	960	1.03	6.816	9.94×10^4	133.12	193.4	no flow

Note: catalyst 10: 0.002 mmol, PMAO-IP: 2 mmol, toluene: 100 mL, 0.5 - 1 hr., RT.
a. 60 $^{\circ}C$.

5

Examples 71-78

Copolymerization of 1-hexene and ethylene

In a dry-box, 0.02 mmol of the catalyst and 30 mL of 1,2,4-trichlorobenzene or toluene were placed in a 100 mL Schlenk flask. The flask was cooled in a freezer in the dry-box and the 1,2,4-trichlorobenzene or toluene was frozen or cooled after 20 min. Then, 5 mL of 1-hexene and cocatalyst PMAO-IP were added to the flask. The flask was sealed, removed from the dry-box and attached to an ethylene Schlenk line. After pumping off the air and nitrogen and purging with ethylene, the reaction mixture was stirred 1 h or overnight depend on the rate of the polymer formation under 5 psi ethylene. The reaction was quenched with 50 mL of a methanol solution of concentrated HCl (10% volume). The polymer was collected on a frit, washed with methanol and acetone thoroughly, and then dried in vacuo overnight.

Most of the polymerizations produced high molecular weight rubbery polymer with high molecular weight and broad molecular weight distribution. The detailed data are listed in Table 4.

25

Table 4. Copolymerization of Ethylene and Hexene

Examp e	Catalyst	PE (g)	T _m (°C)	ΔH _f (J/g)	Me/1000 CH ₂	M _w (M _w / M _n)	MI
71a	1	4.3914	123.29	51.73	32.8	-	0.03
72a	2	1.0443	130.18	162.3	26.2	-	no flow
73a	4	3.6378	122.99	34.9	71.3	240000 (17)	0.6
74a	5	0.893	128.33	135.3	10.2	195000 (multi modal)	-
75b	7	1.7465	119.85	46.19	52.9	557000 (6)	0.075
76b	11	0.4675	129.56	114.8	56.7	-	-
77b	10	3.2786	124.15	4.436	62.5	69546 (17)	no flow
78c	20	3.7811	128.75	134.1	13.2	-	no flow

Note: a. 1-hexene: 5 mL, 1,2,4-trichlorobenzene: 30 mL; b. 1-hexene: 10 mL, toluene: 20 mL; c. 1-hexene: 5 mL, toluene: 40 mL.

5

Examples 79-81Copolymerization of 4-Methyl-1-pentene and Ethylene


In a dry-box, 5 mL of 4-methyl-1-pentene, PMAO-IP, and 30 mL toluene were placed in a 100 mL Schlenk flask and stirred 5 min. Then, 0.02 mmol of the catalyst were added to the flask. The flask was sealed, removed from the dry-box and attached to an ethylene Schlenk line. After pumping off the air and nitrogen and purging with ethylene, the reaction mixture was stirred 1 h or overnight depend on the rate of the polymer formation under 35 kPa ethylene. The reaction was quenched with 50 mL of a methanol solution of concentrated HCl (10% volume). The polymer was collected on a frit, washed with methanol and acetone thoroughly and then dried in vacuo overnight.

Most of the polymerizations produced high molecular weight rubbery polymer and wide molecular weight distribution (for Example 60, M_w = 149517 and M_w/M_n = 63). The detailed data are listed in Table 5.

Table 5. Copolymerization of Ethylene and 4-Methyl-1-pentene

Example	Catalyst	PE (g)	T _m (°C)	ΔH _f (J/ g)	Me/1000 CH ₂	MI
79	11	0.5236	127.09	152.6	62.9	-
80	16	4.8118	120.75	39.55	127	33
81	20	3.6868	128.67	138.8	22.2	no flow

Examples 82-90

Polymerization of Ethylene with Mixed Catalysts

5

In a dry-box, 2 mmol PMAO-IP was added to 40 mL toluene and stirred 5 min. A toluene solution of 0.002-0.004 mmol of the amidinate catalyst **16** and tridentate Fe catalyst (in the above equation, which is believed to produce α -olefin in situ) were added to the flask. The flask was sealed, removed from the dry-box and attached to a Schlenk line which could be filled with ethylene. After pumping off the air and nitrogen and purging with ethylene, the reaction mixture was stirred ~3 h. under 35 kPa ethylene. The reaction was quenched with 50 mL of a methanol solution of concentrated HCl (10% volume). The polymer was collected on a frit, washed with methanol and acetone thoroughly and then dried in vacuo overnight.

20

The polyethylene formed was high in molecular weight, but T_m are decreased compare to the polymer produced from single amidinate catalysts. The detailed data are listed in Table 6.

Table 6. Polymerization of Ethylene by Mixed Catalysts

Example	Catalyst ratio (Ti:Fe)	PE (g)	Productivity (mol PE/mol complex)	T _m (°C)	ΔH _f (J/g)	Me/1000 CH ₂	MI
82	1	11.7452 (4.6652)	4.70 x 10 ⁴ (1.87 x 10 ⁴)	85.15 122.25	166.7 18.3	23.8	17
83 ^b	1	11.5747 (4.0383)	5.37 x 10 ⁴ (1.87 x 10 ⁴)	87.44 119.03	199.8 15.9	26	flow out
84	30	3.555	1.06 x 10 ⁵	126.47	147.1	10.37	no flow
85	15.2	3.1158	8.21 x 10 ⁴	72.19 121.65	141.16 23.64	30	2.6
86	8	3.1737	8.38 x 10 ⁴	124.12	170.2	12.2	no flow
87 ^c	9.8	0.3713	8825	78.45 114.28 125.82	22.84 117.14 30.52	17.9	-
88 ^c	3.65	1.9637	1.41 x 10 ⁴	77.91 119.67	86.54 95.03	6.59	0.73
89 ^d	21	16.054	2.35 x 10 ⁵	118.9	141.1	7.05	no flow
90 ^d	7.78	18.253	3.25 x 10 ⁵	123.64	147.5	23.7	no flow

Note: a. mixture of α-olefin and polymer; b. 40 °C; c. 60 °C; d. 1.03 MPa, 80 °C, catalyst 10 instead of 16.

5

Examples 91 -94

Polymerization of 1-hexene

In a dry-box, 0.02 mmol of the catalyst and 7.66 mL of 1,2,4-trichlorobenzene were placed in a 20 mL glass vial.

- 10 Three mL of 1-hexene was added to the vial. Then, 2.34 mL (10 mmol) of PMAO was quickly added to the vial. After being stirred at RT 48 h, the reaction mixture was taken out from the dry-box and slowly poured to a beaker containing 50 mL of a methanol solution of concentrated HCl (10% volume). The
- 15 colorless waxy polymer was separated from the methanol solution, washed with methanol and acetone thoroughly and then dried in vacuo overnight.

Table 7. Polymerization of 1-Hexene

Example	Catalyst	Polymer (g)	Productivity (mol PH / mol complex)	M _w (M _w / M _n)
91	1	0.2001	118	
92	2	0.2803	165	50900 (47)
93	4	0.3356	305	2130 (15)
94	5	0.0838	57	

Examples 95-97Polymerization of propylene

In a dry-box, 0.01 mmol of the catalyst was placed in a 50 mL Schlenk flask with threaded joints and 20 mL of toluene was added to dissolve or partially dissolve the catalyst. The flask was sealed, removed from the dry-box and attached to an propylene line. After purging with nitrogen and propylene, 2.33 mL (10 mmol) of PMAO was quickly added to the flask under about 35 kPa propylene. After being stirred at RT 48 h, the reaction mixture was quenched with 50 mL of a methanol solution of concentrated HCl (10% volume). The polymer was collected on a frit, washed with methanol and acetone thoroughly and then dried in vacuo overnight.

Table 8. Polymerization of propylene

Example	Catalyst	Polymer (g)	Productivity (mol PP / mol complex)	M _w (M _w / M _n)
95	1	0.2184	503	180000 (multi modal)
96	2	0.2344	366	260000 (multi modal)
97	5	0.0931	188	188000 (multi modal)

Examples 98-99Polymerization of Norbornene

In a dry-box, to a 20 mL glass vial containing 2.26 g (0.04 mol) of norbornene and 3 mL of toluene, was added 2.34 mL (10 mmol) PMAO. The mixture was stirred 5 min and then 4.66 mL of a toluene suspension of the catalyst (0.02 mmol) was added. After being stirred at RT 24 h, the reaction mixture was taken out from the dry-box and slowly poured to a beaker containing 50 mL of a methanol solution of concentrated HCl (10% volume). The polymer was collected on

a frit, washed with methanol and acetone thoroughly and then dried in vacuo overnight.

Table 9. Polymerization of norbornene

Example	Catalyst	Polymer (g) (Conversion %)	Productivity (mol PN/ mol complex)	M _w (M _w / M _n)
98	1	0.4325 (19.1)	333	96500 (multi modal)
99	2	0.5072 (22.4)	227	133000 (multi modal)

5

Example 100

Preparation of Azobenzene-Bridged Bis-guanidinate Ligand and Zirconium Complex

Azobenzene (2.73 g, 15 mmol) was dissolved in THF (30 mL) under nitrogen in a drybox. Lithium metal (0.36 g, 50 mmol) was added to the solution. The orange changed to green before turning to orange-brown. After three h stirring, the solution was added slowly to a solution of bis(trimethylsilyl)carbodiimide (5.59 g, 30 mmol) causing a slight lightening of the solution color. Stirring was continued for 30 min.

The resulting solution was added slowly to a THF (30 mL) solution of ZrCl₄ (3.5 g, 15 mmol). There was a slight darkening to dark beige. The THF was removed under vacuum and the solid was extracted with methylene chloride. Filtration through filter aid gave a yellow-gray solution which was taken to dryness. The solid was then suspended in ether, filtered and dried under vacuum. Yield: 1.7g

The ether solution was stripped to dryness yielding a very small quantity of a white solid which crystallized like an organic. The ¹H NMR indicated the presence of phenyl and trimethylsilyl resonances in a 1:1 ratio with no other signals. The solid was taken up in ether and placed in the drybox freezer where it crystallized. X-ray analysis demonstrated that it was 1,2-diphenyl-1,2-bis(trimethylsilyl)hydrazine.

Example 101

Polymerization With an Azobenzene-Bridged Bis-guanidinate Zirconium Complex

In toluene (35 mL), catalyst (0.0122 g, 0.02 mmol) with 2.22 mL of MMAO (10 mmol) at RT and 1 atm ethylene overnight yielded 1.51 g of HDPE polyethylene.

Example 102Preparation of Azobenzene-Bridged Bis-guanidinate Ligand and
Titanium Complex

5 Azobenzene (2.73 g, 15 mmol) was dissolved in THF (30 mL) under nitrogen in a drybox. Lithium metal (0.36 g, 50 mmol) was added to the solution. The orange changed to green before turning to orange-brown. After three h stirring, the solution was added slowly to a solution of
10 bis(trimethylsilyl)carbodiimide (5.59 g, 30 mmol) causing a slight lightening of the solution color. Stirring was continued for 30 min.

The resulting solution was reacted with a THF (30 mL) solution of $\text{TiCl}_4 \cdot 2\text{THF}$ (3.5 g, 15 mmol). There was a rapid darkening to red-brown. The THF was removed under vacuum and
15 the solid was extracted repeatedly with methylene chloride. Filtration through filter aid gave a deep red-brown solution which was taken to dryness. Yield: 1.23 g. Washing with ether yielded a trace material having the same NMR as
20 observed for diphenyl-bis-trimethylsilylhydrazine as noticed in the zirconium reaction.

Example 103Polymerization With an Azobenzene-Bridged Bis-guanidinate
Titanium Complex

25 In toluene (35 mL), 0.02 mmol of catalyst with 2.22 mL of MMAO (10 mmol) at RT and 1 atm ethylene overnight yielded 0.38 g of polyethylene. In trichlorobenzene, 0.0050 g of catalyst with 3 mL of MMAO at 50°C and 1.38 MPa ethylene
30 yielded 4.112 g of polyethylene, which was "No flow" MI and had 10.8 Me/1000CH₂.

Example 104Preparation of butadiene-bridged bis-amidinate ligand and
titanium complex

35 Magnesium butadiene (15 mmol) is prepared according to the method of Yasuda (J. Organomet. Chem., 113, 201 (1976)). The resulting solution is added slowly to a solution of

bis(trimethylsilyl)carbodiimide (5.59 g, 30 mmol). Stirring is continued for 30 min.

The resulting solution is reacted with a THF (30 mL) solution of $\text{TiCl}_4 \cdot 2\text{THF}$ (3.5 g, 15 mmol). The THF is removed under vacuum and the solid is extracted repeatedly with methylene chloride. Filtration through filter aid gives a deep red-brown solution which is taken to dryness yielding a powder.

10

Example 105


Polymerization With a Butadiene-Bridged Bis-amidinate Titanium Complex

In toluene (35 mL), 0.02 mmol of catalyst is reacted with 2.22 mL of MMAO (10 mmol) at RT and pressurized with 1 atm ethylene. The resulting polymerization yields high density polyethylene.

CLAIMS

What is claimed is:

1. A process for the polymerization of olefins, comprising the step of contacting, at a temperature of about -50°C to about +250°C, (a) an olefin selected from the group consisting of an α -olefin, a styrene, a cyclopentene, and a norbornene; and (b) a catalyst component for the polymerization of the olefin, characterized in that the catalyst component comprises a first compound of the formula (X)



wherein:

R^1 , R^2 , R^3 and R^4 are each independently hydrocarbyl, substituted hydrocarbyl or silyl;

R^{15} is a divalent organic moiety;

each X is independently an anion;

n is an integer equal to the valence of M minus 2; and


M is Ti, Zr, Hf, V, Cr, Sc, Y or a rare earth metal.

2. The process as recited in claim 1, characterized in that the catalyst component further comprises a second compound W, which is a neutral Lewis acid capable of abstracting an X^- from the first compound to form WX^- , provided that the anion formed is a weakly coordinating anion, or a cationic Lewis or Bronsted acid whose counterion is a weakly coordinating anion; and provided that when none of X is alkyl, acyl or hydride, said second compound is capable of transferring hydride or alkyl to M.

3. A process for the polymerization of olefins, comprising the step of contacting, at a temperature of about -50°C to about +250°C, (a) an olefin selected from the group

consisting of an α -olefin, a styrene, a cyclopentene, and a norbornene; and (b) a catalyst component for the polymerization of the olefin,

characterized in that the catalyst component comprises a transition metal complex of a ligand of the formula (XI)






wherein:

said transition metal is Ti, Zr, Hf, V, Cr, Sc, Y or a rare earth metal;

R^1 , R^2 , R^3 and R^4 are each independently hydrocarbyl, substituted hydrocarbyl or silyl; and R^{15} is a divalent organic moiety.

4. The process as recited in any one of claims 1-3, characterized in that R^{15} is



wherein:

R^5 , R^6 , R^7 and R^8 are each independently hydrogen, hydrocarbyl or substituted hydrocarbyl, provided that either or both of the pairs R^5 and R^6 , and R^7 and R^8 taken together may form a ring;

R^9 , R^{10} , R^{11} and R^{12} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or a functional group, provided that any two of R^9 , R^{10} , R^{11} and R^{12} vicinal to one another may form a ring;

each R¹⁶ is hydrogen;
and q is 4.

5 5. The process as recited in any one of claims 1-3,
characterized in that R¹, R², R³ and R⁴ are each
independently alkyl or silyl.

6. The process as recited in claim 4, characterized in
that R⁵, R⁶, R⁷ and R⁸ are each independently alkyl or
10 hydrogen; and R⁹, R¹⁰, R¹¹ and R¹² are all hydrogen.

7. The process as recited in any one of claims 1-3,
characterized in that said olefin is an α -olefin.

15 8. The process as recited in claim 7, characterized in
that the α -olefin is ethylene.


9. The process as recited in claim 8, characterized in
that a catalyst which oligomerizes ethylene to an α -olefin is
20 also present.

10. The process as recited in any one of claims 1-3,
characterized in that M is Zr or Ti.

25 11. The process as recited in any one of claims 1-3,
characterized in that the catalyst component comprises
another active olefin polymerization catalyst.

12. The process as recited in claim 11, characterized in
30 that the another active olefin polymerization catalyst
comprises a late transition metal catalyst, a Ziegler-Natta
catalyst and/or a metallocene-type catalyst.


13. An anion of the formula



wherein:

R^1 , R^2 , R^3 and R^4 are each independently hydrocarbyl,
 5 substituted hydrocarbyl or silyl; and
 R^{15} is a divalent organic moiety.

14. A compound of the formula:



10 wherein:



R^1 , R^2 , R^3 and R^4 are each independently hydrocarbyl,
 substituted hydrocarbyl or silyl;


R^{15} is a divalent organic moiety;

each X is independently an anion;

15 n is an integer equal to the valence of M minus 2; and
 M is Ti, Zr, Hf, V, Cr, Sc, Y or a rare earth metal.

15. The anion as recited in claim 13, or the compound as
 recited in claim 14, characterized in that R^{15} is





wherein:

5 R^5 , R^6 , R^7 and R^8 are each independently hydrogen, hydrocarbyl or substituted hydrocarbyl, provided that either or both of the pairs R^5 and R^6 , and R^7 and R^8 taken together may form a ring;

R^9 , R^{10} , R^{11} and R^{12} are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or a functional group, provided that any two of R^9 , R^{10} , R^{11} and R^{12} vicinal to one
10 another may form a ring;

each R^{16} is hydrogen;

and q is 4.

15 16. The anion as recited in claim 13, or the compound as recited in claim 14, characterized in that R^1 , R^2 , R^3 and R^4 are each independently alkyl or silyl.

20 17. The anion as recited in claim 15, or the compound as recited in claim 15, characterized in that R^5 , R^6 , R^7 and R^8 are each independently alkyl or hydrogen; and R^9 , R^{10} , R^{11} and R^{12} are all hydrogen.

25 18. The compound as recited in claim 14, characterized in that M is Ti or Zr .

19. A process for the production of a bis(carboximidamidonate), comprising the step of reacting a bis(alkyl metal salt) with 2 moles of a carbodiimide.

30 20. The process as recited in claim 20, characterized in that said metal is magnesium.

35 21. A process for preparing a transition metal complex of a bis(carboximidamidonate), comprising the step of reacting a salt of said transition metal with a dialkali metal salt or alkaline earth metal salt of a bis(carboximidamidonate).

22. The process as recited in claim 22, characterized in that said dialkali metal salt or alkaline earth metal salt of a bis(carboximidamidatonate) is a magnesium salt.

5 23. The process as recited in claim 22, characterized in that said transition metal is Ti, Zr, Hf, V, Cr, Sc, Y or a rare earth metal.

INTERNATIONAL SEARCH REPORT

Inte: onal Application No

PCT/U 9/19954

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 C08F4/62 C08F4/70 C08F10/02 C07F19/00 C07C257/14
C07F7/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F C07F C07C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 763 550 A (SHOWA DENKO KK) 19 March 1997 (1997-03-19) abstract page 13, line 10 - line 14 page 9, line 14 - line 23 page 11 formula 20 page 11, line 56 -page 12, line 14	1-3,5,7, 8,10,11, 13,14, 16,18
X	BUSCH, M. HOBEIN, R.: "Magnesiumhalogenalkyl und Carbodiimide" BERICHTE DER DEUTSCHEN CHEMISCHEN GESELLSCHAFT, vol. 40, 1907, pages 4296-4298, XP000865528	19,20
Y	the whole document	21-23
	-/-	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

21 December 1999

Date of mailing of the international search report

12/01/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Gamb, V

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US99/19954

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	<p>HERSKOVICS-KORINE D ET AL: "Bis(trimethylsilyl)benzamidinate zirconium dichlorides. Active catalysts for ethylene polymerization". JOURNAL OF ORGANOMETALLIC CHEMISTRY, CH, ELSEVIER-SEQUOIA S.A. LAUSANNE, vol. 503, no. 2, page 307-314 XP004023639 ISSN: 0022-328X cited in the application abstract page 308</p>	21-23
E	<p>WO 99 50318 A (CITRON JOEL DAVID ; COUGHLIN EDWARD BRYAN (US); DU PONT (US); WANG) 7 October 1999 (1999-10-07) page 25 : compounds S, T, U and V page 31, table 4 : examples 38-41 claims 1-20</p>	1-18

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/99/19954

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0763550 A	19-03-1997	DE 69602329 D	10-06-1999
		DE 69602329 T	23-09-1999
		JP 9136912 A	27-05-1997
		US 5723399 A	03-03-1998
WO 9950318 A	07-10-1999	NONE	

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☒ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.